

# Versaflex™ CL30

## Thermoplastic Elastomer

### Key Characteristics

#### Product Description

Versaflex™ CL30 is an easy processing compound designed for use in injection molding and extrusion applications where water-clarity and excellent colorability are required.

- Excellent Clarity
- Excellent Colorability
- Overmold Adhesion to Polypropylene
- Soft Touch

#### General

Material Status	• Commercial: Active		
Regional Availability	• Africa & Middle East • Asia Pacific	• Latin America • North America	
Features	• Good Colorability	• High Clarity	
Uses	• Consumer Applications • Flexible Grips	• Optical Applications • Overmolding	• Soft Touch Applications • Transparent or Translucent Parts
Agency Ratings	• FDA Unspecified Rating		
RoHS Compliance	• RoHS Compliant		
Appearance	• Clear/Transparent		
Forms	• Pellets		
Processing Method	• Injection Molding		

### Technical Properties <sup>1</sup>

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	0.890	0.890	ASTM D792
Melt Mass-Flow Rate (MFR)			ASTM D1238
190°C/2.16 kg	18 g/10 min	18 g/10 min	
200°C/5.0 kg	108 g/10 min	108 g/10 min	
Molding Shrinkage - Flow	0.021 to 0.025 in/in	2.1 to 2.5 %	ASTM D955
Elastomers	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Stress <sup>2, 3</sup> (100% Strain, 73°F (23°C))	100 psi	0.689 MPa	ASTM D412
Tensile Stress <sup>2, 3</sup> (300% Strain, 73°F (23°C))	200 psi	1.38 MPa	ASTM D412
Tensile Strength <sup>2, 3</sup> (Break, 73°F (23°C))	751 psi	5.18 MPa	ASTM D412
Tensile Elongation <sup>2, 3</sup> (Break, 73°F (23°C))	870 %	870 %	ASTM D412
Tear Strength	110 lbf/in	19.3 kN/m	ASTM D624
Compression Set (73°F (23°C), 22 hr)	11 %	11 %	ASTM D395B
Hardness	Typical Value (English)	Typical Value (SI)	Test Method
Durometer Hardness (Shore A, 10 sec)	30	30	ASTM D2240
Fill Analysis	Typical Value (English)	Typical Value (SI)	Test Method
Apparent Viscosity			ASTM D3835
392°F (200°C), 11200 sec <sup>-1</sup>	14.8 Pa·s	14.8 Pa·s	

Copyright © 2020 Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. Avient makes no warranties or guarantees respecting suitability of either Avient's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. Avient MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.

## Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Suggested Max Regrind	20 %	20 %
Rear Temperature	320 to 370 °F	160 to 188 °C
Middle Temperature	350 to 390 °F	177 to 199 °C
Front Temperature	360 to 440 °F	182 to 227 °C
Nozzle Temperature	370 to 440 °F	188 to 227 °C
Mold Temperature	60 to 100 °F	16 to 38 °C
Back Pressure	0.00 to 125 psi	0.00 to 0.862 MPa
Screw Speed	75 to 125 rpm	75 to 125 rpm

## Injection Notes

Color concentrates with polypropylene (PP), ethylene vinyl acetate (EVA), or polyethylene (PE) carriers are most suitable for coloring Versaflex™ CL30. Improved color dispersion can be achieved by using higher melt flow concentrates (with a melt flow from 25 - 40 g/10 min). Typical loadings for color concentrates are 1% to 5% by weight. Liquid color can be used, but mineral oil based carriers may have a significant effect on the final hardness value. Concentrates based on PVC should not be used. A high color match consistency can be obtained by using precolored compounds available from GLS. The final determination of color concentrate suitability should be determined by customer trials.

Purge thoroughly before and after use of this product with a low flow (0.5 - 2.5 MFR) polyethylene (PE) or polypropylene (PP).

Regrind levels up to 20% can be used with Versaflex™ CL30 with minimal property loss, provided that the regrind is free of contamination. To minimize losses during molding, the melt temperature should remain as low as possible. The final determination of regrind effectiveness should be determined by the customer.

Drying is not Required

Injection Speed: 1 to 5 in/sec

1st Stage - Boost Pressure: 400 to 1000 psi

2nd Stage - Hold Pressure: 30% of Boost

Hold Time (Thick Part): 3 to 10 sec

Hold Time (Thin Part): 1 to 3 sec

## Notes

<sup>1</sup> Typical values are not to be construed as specifications.

<sup>2</sup> Die C

<sup>3</sup> 2 hr

## CONTACT INFORMATION

## North America

Avon Lake, United States  
33587 Walker Road  
Avon Lake, OH, United States ,  
44012  
+1 440 930 1000  
+1 844 4AVIENT

## South America

Sao Paulo, Brazil  
Av. Francisco Nakasato, 1700  
13295-000 Itupeva  
Sao Paulo, Brazil  
+55 11 4593 9200

## Asia

Shanghai, China  
2F, Block C  
200 Jinsu Road  
Pudong, 201206  
Shanghai, China  
+86 (0) 21 6028 4888

## Europe

Pommerloch, Luxembourg  
19 Route de Bastogne  
Pommerloch, Luxembourg , L-9638  
+352 269 050 35



avient.com

Copyright © 2020 Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. Avient makes no warranties or guarantees respecting suitability of either Avient's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. Avient MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.