

Versaflex™ OM 6160-9

Thermoplastic Elastomer

Key Characteristics

Product Description

Versaflex™ OM 6160-9 is specifically designed to bond to a variety of standard and modified nylon materials, including those which are glass-filled, heat stabilized and/or impact modified.

- Excellent Surface Appearance
- Outstanding Adhesion in Both Two-Shot and Insert Molding Processes
- Soft, Rubbery Grip
- Very Easy to Process

General

Material Status	• Commercial: Active		
Regional Availability	• Africa & Middle East • Asia Pacific	• Latin America • North America	
Features	• Good Adhesion	• Good Processability	• Good Surface Finish
Agency Ratings	• UL 94		
Appearance	• Black		
Processing Method	• Injection Molding		

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	1.11	1.11	ASTM D792
Melt Mass-Flow Rate (MFR)			ASTM D1238
190°C/2.16 kg	5.0 g/10 min	5.0 g/10 min	
200°C/5.0 kg	38 g/10 min	38 g/10 min	
Molding Shrinkage - Flow	0.017 to 0.021 in/in	1.7 to 2.1 %	ASTM D955
Elastomers	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Stress ^{2, 3} (100% Strain, 73°F (23°C))	330 psi	2.28 MPa	ASTM D412
Tensile Stress ^{2, 3} (300% Strain, 73°F (23°C))	428 psi	2.95 MPa	ASTM D412
Tensile Strength ^{2, 3} (Break, 73°F (23°C))	444 psi	3.06 MPa	ASTM D412
Tensile Elongation ^{2, 3} (Break, 73°F (23°C))	370 %	370 %	ASTM D412
Tear Strength	140 lbf/in	24.5 kN/m	ASTM D624
Compression Set (73°F (23°C), 22 hr)	31 %	31 %	ASTM D395B
Hardness	Typical Value (English)	Typical Value (SI)	Test Method
Durometer Hardness (Shore A, 10 sec)	60	60	ASTM D2240
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Flame Rating (0.06 in (1.5 mm))	HB	HB	UL 94
Fill Analysis	Typical Value (English)	Typical Value (SI)	Test Method
Apparent Viscosity			ASTM D3835
392°F (200°C), 11200 sec ⁻¹	19.6 Pa·s	19.6 Pa·s	

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Suggested Max Re grind	20 %	20 %
Rear Temperature	330 to 380 °F	166 to 193 °C

Copyright © 2020 Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. Avient makes no warranties or guarantees respecting suitability of either Avient's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. Avient MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.

Injection	Typical Value (English)	Typical Value (SI)
Middle Temperature	480 to 500 °F	249 to 260 °C
Front Temperature	490 to 530 °F	254 to 277 °C
Nozzle Temperature	490 to 530 °F	254 to 277 °C
Processing (Melt) Temp	500 to 530 °F	260 to 277 °C
Mold Temperature	60 to 100 °F	16 to 38 °C
Back Pressure	0.00 to 100 psi	0.00 to 0.689 MPa
Screw Speed	75 to 175 rpm	75 to 175 rpm

Injection Notes

Purge thoroughly before and after use of this product with a low flow (0.5 - 2.5 MFR) polyethylene (PE) or polypropylene (PP).

Regrind levels up to 20% can be used with Versaflex™ OM 6160-9 with minimal property loss, provided that the regrind is free of contamination. To minimize losses during molding, the melt temperature should remain as low as possible. The final determination of regrind effectiveness should be determined by the customer.

Versaflex™ OM 6160-9 has good melt stability. Maximum residence times may vary, depending on the size of the barrel. Generally, the barrel should be emptied if it is idle for periods of 8 - 10 minutes or longer.

Drying is not Required

Injection Speed: 2.5 to 5 in/sec
 1st Stage - Boost Pressure: 400 to 600 psi
 2nd Stage - Hold Pressure: 30% of Boost
 Hold Time (Thick Part): 3 to 6 sec
 Hold Time (Thin Part): 1 to 3 sec

Notes

¹ Typical values are not to be construed as specifications.

² Die C

³ 2 hr

CONTACT INFORMATION**North America**

Avon Lake, United States
 33587 Walker Road
 Avon Lake, OH, United States ,
 44012
 +1 440 930 1000
 +1 844 4AVIENT

South America

Sao Paulo, Brazil
 Av. Francisco Nakasato, 1700
 13295-000 Itupeva
 Sao Paulo, Brazil
 +55 11 4593 9200

Asia

Shanghai, China
 2F, Block C
 200 Jinsu Road
 Pudong, 201206
 Shanghai, China
 +86 (0) 21 6028 4888

Europe

Pommerloch, Luxembourg
 19 Route de Bastogne
 Pommerloch, Luxembourg , L-9638
 +352 269 050 35



avient.com

Copyright © 2020 Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. Avient makes no warranties or guarantees respecting suitability of either Avient's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. Avient MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.