

Versaflex™ OM 6275-1

Thermoplastic Elastomer

Key Characteristics

Product Description

Versaflex™ OM 6275-1 is specifically designed to bond to a variety of standard and modified nylon materials, including those which are glass-filled, heat stabilized and/or impact modified.

New Product. Commercial specifications have not been established.

- Exceptional Colorability
- Outstanding Adhesion in Both Two-Shot and Insert Molding Processes
- Outstanding Adhesion in Both Two-Shot and Insert Molding Processes
- Soft, Rubbery Grip
- Very Easy to Process

General

Material Status	• Commercial: Active		
Regional Availability	• Africa & Middle East	• Latin America	• North America
Features	• Good Adhesion	• Good Colorability	• Good Processability
Appearance	• Natural Color		
Processing Method	• Injection Molding		

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	1.10	1.10	ASTM D792
Molding Shrinkage - Flow	0.014 to 0.020 in/in	1.4 to 2.0 %	ASTM D955
Elastomers	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Stress ^{2, 3} (100% Strain, 73°F (23°C))	480 psi	3.31 MPa	ASTM D412
Tensile Stress ^{2, 3} (300% Strain, 73°F (23°C))	630 psi	4.34 MPa	ASTM D412
Tensile Strength ^{2, 3} (Break, 73°F (23°C))	580 psi	4.00 MPa	ASTM D412
Tensile Elongation ^{2, 3} (Break, 73°F (23°C))	260 %	260 %	ASTM D412
Tear Strength	165 lbf/in	28.9 kN/m	ASTM D624
Compression Set (73°F (23°C), 22 hr)	25 %	25 %	ASTM D395B
Hardness	Typical Value (English)	Typical Value (SI)	Test Method
Durometer Hardness (Shore A, 10 sec)	75	75	ASTM D2240
Fill Analysis	Typical Value (English)	Typical Value (SI)	Test Method
Apparent Viscosity 392°F (200°C), 11200 sec ⁻¹	36.0 Pa·s	36.0 Pa·s	ASTM D3835

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Suggested Max Regrind	20 %	20 %
Rear Temperature	360 to 400 °F	182 to 204 °C
Middle Temperature	470 to 510 °F	243 to 266 °C
Front Temperature	480 to 520 °F	249 to 271 °C
Nozzle Temperature	490 to 530 °F	254 to 277 °C
Processing (Melt) Temp	480 to 520 °F	249 to 271 °C

Copyright © 2020 Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. Avient makes no warranties or guarantees respecting suitability of either Avient's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. Avient MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.

Injection	Typical Value (English)	Typical Value (SI)
Mold Temperature	55 to 85 °F	13 to 29 °C
Back Pressure	0.00 to 80.0 psi	0.00 to 0.552 MPa
Screw Speed	80 to 120 rpm	80 to 120 rpm

Injection Notes

Color concentrates with EVA or LDPE carriers are most suitable for coloring Versaflex™ OM 6275-1. Typical ratios are 50:1 to 25:1 - loading levels should be as low as possible to minimize the effect on adhesion. A high color match consistency can be obtained by the use of precolored compounds available from GLS. Polypropylene (PP) based color concentrates are not recommended because they can significantly affect adhesion of the TPE to the nylon. Concentrates based on PVC should not be used. The final determination of color concentrate suitability should be determined by customer trials.

Purge thoroughly before and after use of this product with a low flow (0.5 - 2.5 MFR) polyethylene (PE) or polypropylene (PP).

Regrind levels up to 20% can be used with Versaflex™ OM 6275-1 with minimal property loss, provided that the regrind is free of contamination. To minimize losses during molding, the melt temperature should remain as low as possible. The final determination of regrind effectiveness should be determined by the customer.

Versaflex™ OM 6275-1 has good melt stability. Maximum residence times may vary, depending on the size of the barrel. Generally, the barrel should be emptied if it is idle for periods of 8 - 10 minutes or longer.

Drying is not Required

Injection Speed: 3 to 5 in/sec
 1st Stage - Boost Pressure: 300 to 800 psi
 2nd Stage - Hold Pressure: 0% of Boost
 Hold Time (Thick Part): 0 to 4 sec
 Hold Time (Thin Part): 0 to 3 sec

Notes

¹ Typical values are not to be construed as specifications.

² Die C

³ 2 hr

CONTACT INFORMATION**North America**

Avon Lake, United States
 33587 Walker Road
 Avon Lake, OH, United States ,
 44012
 +1 440 930 1000
 +1 844 4AVIENT

South America

Sao Paulo, Brazil
 Av. Francisco Nakasato, 1700
 13295-000 Itupeva
 Sao Paulo, Brazil
 +55 11 4593 9200

Asia

Shanghai, China
 2F, Block C
 200 Jinsu Road
 Pudong, 201206
 Shanghai, China
 +86 (0) 21 6028 4888

Europe

Pommerloch, Luxembourg
 19 Route de Bastogne
 Pommerloch, Luxembourg , L-9638
 +352 269 050 35



avient.com

Copyright ©, 2020 Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. Avient makes no warranties or guarantees respecting suitability of either Avient's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. Avient MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.