

Versaflex™ CE 3620

Thermoplastic Elastomer

Key Characteristics

Product Description

Versaflex™ CE 3620 is targeted for consumer electronics applications where abrasion resistance, UV resistance and enhanced feel are required.

Versaflex™ CE 3620 can also overmold to a variety of substrates including PC,ABS, PC/ABS and Copolyester.

General

Material Status	• Commercial: Active		
Regional Availability	• Africa & Middle East	• Asia Pacific	• North America
Features	• Abrasion Resistant • Chemical Resistant • Good Colorability	• Good Processability • Low Friction • Paintable	• UV Resistant
Uses	• Appliances • Communication Applications • Computer Components • Consumer Applications	• Electrical/Electronic Applications • Flexible Grips • Overmolding • Soft Touch Applications	• Thick-walled Parts • Thin-walled Parts
Agency Ratings	• ISO 10993 Part 10 ¹		
RoHS Compliance	• RoHS Compliant		
Appearance	• Black	• Natural Color	
Forms	• Pellets		
Processing Method	• Injection Molding		

Technical Properties²

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	1.00	1.00	ASTM D792
Melt Mass-Flow Rate (MFR)			ASTM D1238
190°C/2.16 kg	2.0 to 15 g/10 min	2.0 to 15 g/10 min	
200°C/5.0 kg	25 to 35 g/10 min	25 to 35 g/10 min	
Molding Shrinkage - Flow	0.011 to 0.017 in/in	1.1 to 1.7 %	ASTM D955
Elastomers	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Stress ^{3,4} (100% Strain)	442 psi	3.05 MPa	ASTM D412
Tensile Stress ^{3,4} (300% Strain)	618 psi	4.26 MPa	ASTM D412
Tensile Strength ^{3,4} (Break)	1020 psi	7.03 MPa	ASTM D412
Tensile Elongation ^{3,4} (Break)	630 %	630 %	ASTM D412
Tear Strength ^{3,4}	232 lbf/in	40.6 kN/m	ASTM D624
Compression Set ⁵ (73°F (23°C), 22 hr)	18 %	18 %	ASTM D395
Hardness	Typical Value (English)	Typical Value (SI)	Test Method
Shore Hardness (Shore A, 10 sec)	65	65	ASTM D2240
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Flame Rating			UL 94
0.06 to 0.51 in (1.5 to 13.0 mm), All Colors	HB	HB	
Fill Analysis	Typical Value (English)	Typical Value (SI)	Test Method
Apparent Viscosity (392°F (200°C))	19.4 Pa·s	19.4 Pa·s	ASTM D3835

Copyright © 2020 Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. Avient makes no warranties or guarantees respecting suitability of either Avient's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. Avient MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.

Additional Information	Typical Value (English)	Typical Value (SI)
Generic Material Type	Thermoplastic Elastomer	Thermoplastic Elastomer

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	125 to 140 °F	52 to 60 °C
Drying Time	1.0 to 3.0 hr	1.0 to 3.0 hr
Suggested Max Moisture	0.020 to 0.030 %	0.020 to 0.030 %
Suggested Max Regrind	20 %	20 %
Rear Temperature	340 to 360 °F	171 to 182 °C
Middle Temperature	360 to 430 °F	182 to 221 °C
Front Temperature	370 to 440 °F	188 to 227 °C
Nozzle Temperature	380 to 460 °F	193 to 238 °C
Processing (Melt) Temp	380 to 450 °F	193 to 232 °C
Mold Temperature	55 to 110 °F	13 to 43 °C
Back Pressure	0.00 to 50.0 psi	0.00 to 0.345 MPa
Screw Speed	50 to 100 rpm	50 to 100 rpm

Injection Notes

Typical colorant letdown ratios are 50:1 to 25:1 – loading levels should be as low as possible to minimize the effect on adhesion. A high color match consistency can be obtained by the use of pre-colored compounds available from GLS. Concentrates based on PVC should not be used. The final determination of color concentrate suitability should be determined by customer trials. Contact GLS for more information on appropriate color concentrate base resins.

Purge thoroughly before and after use of this product with a low flow (0.5 - 2.5 MFR) polyethylene (PE) or polypropylene (PP).

Regrind levels of up to 20% can be used with Versaflex™ CE 3620 with minimal property loss, provided that the regrind is free of contamination. To minimize losses during molding, the melt temperature should remain as low as possible. The final determination of regrind effectiveness should be determined by the customer.

Versaflex™ CE 3620 should not be left in the barrel for extended idle periods (greater than 5 minutes).

Suggested Dewpoint: -40°F

Injection Speed: 0.5 to 4 in/sec

1st Stage - Boost Pressure: 500 to 1,000 psi

2nd Stage - Hold Pressure: 20-60% of Boost

Hold Time (Thick Part): 2 to 4 sec

Hold Time (Thin Part): 1 to 2 sec

Notes

¹ Please contact GLS Thermoplastic Elastomers for a copy of the compliance letter.

PolyOne Corporation does not approve the use of this product in any application classified as medical device, drug packaging or any other application in contact with drugs/pharmaceuticals.

² Typical values are not to be construed as specifications.

³ Die C

⁴ 2 hr

⁵ 25% deflection

CONTACT INFORMATION

North America

Avon Lake, United States
33587 Walker Road
Avon Lake, OH, United States ,
44012
+1 440 930 1000
+1 844 4AVIENT

South America

Sao Paulo, Brazil
Av. Francisco Nakasato, 1700
13295-000 Itupeva
Sao Paulo, Brazil
+55 11 4593 9200

Asia

Shanghai, China
2F, Block C
200 Jinsu Road
Pudong, 201206
Shanghai, China
+86 (0) 21 6028 4888

Europe

Pommerloch, Luxembourg
19 Route de Bastogne
Pommerloch, Luxembourg , L-9638
+352 269 050 35



avient.com

Copyright ©, 2020 Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. Avient makes no warranties or guarantees respecting suitability of either Avient's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. Avient MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.